PRODUCT INFORMATION



NMPfree

WATERBASED

SYNTEKO NovaBEST XC

Extra matt (5), matt (20), semi-gloss (45), gloss (90)

BEST is enhanced with extra ceramics now! Synteko *Nova*BEST is a two-component 100% PU waterborne floor finish for solid timber floors and parquet

AREA OF USE: for all kind of high traffic and commercial areas like offices, shops, etc.

PRODUCT PROPERTIES:

- professional's preferable product perfomance
- optimal wet time in difficult conditions
- excellent levelling
- low VOC, only 60 g/L (max 90 g/L while mixed with Hardener)
- very strong and durablesurface
- excellent friction
- very resistance to scratching, scuffing, chemicals and liquids
- non-yellowing surface

COVERAGE:

8–12 m²/l, depending on tools and wood species.

TOOLS:

- Applicator with mohair felt, approx. 5 mm pile high, 300-500 mm width
- Roller with synthetic material approx 8-10 mm pile high
- Clean tools with water immediately after use.

ATTENTION!

- Waterborne floor finishes must not be covered with solventborne finishes.
- Wood that has been chemically treated or mechanically compressed can not be finished with waterborne finishes.
- Oily and resinous wood species such as teak should be coated immediately after machine sanding.
- Tape must not be used on waterborne finishes.
- All finishes should be shaken before use. Do this before vacuuming so that the air mixed into the finish during shaking has a few minutes to escape before use.
- Do not apply more than two coats per day (sealer and/or finish).
- Direct sunlight should be blocked, also avoid too high or low temperature and humidity
- The finish should be at room temperature when applied. If the finish is too cold, it flows much less freely and also releases air poorly, which can result in brush stroke marks and air bubbles remaining after drying. It takes about seven hours to warm the lacquer from 0°C to 20°C.

TECHNICAL DATA:

BASE MATERIAL	Waterborne polyurethane
HARDENER	Polyisocyanate diluted in dipropyleneglycoldimethyleether
SOLIDS CONTENT	ca. 32% (ISO 3251)
PH	ca. 8,0
VISCOSITY	ca. 24 sec. (ISO 2431)
DENSITY	ca. 1,1 kg/l
SCUFF RESISTANCE	No marks at 5 kp/cm ²
GLOSS	Ca. 5 for extra matte
(measured at 60°)	ca. 20 for matte,
	ca. 45 for semi-gloss,
	ca. 90 for gloss
DRYING TIME	30-60 mins first coat
at 20°C /50% RH	2-3 hours each following coat
	Final strenght after 3 days
POT LIFE OF	ca. 4 hours at 23°C
MIXTURE	
STORAGE	Store frost-free. Must be stored between +10°C and +30°C
SELF LIFE	12 months in unopened container from production date (s. package)
PACKAGE SIZE	5L together with hardener

DURING APPLICATION

- The finish should be at room temperature of approx. 23°C.
- Floor temperature must be between 15 and 25°C.
- Floor moisture content must be between 5 and 15%
- Humidity must be 50 60 % RH

BEFORE USING THE FLOOR

- The floor can be used with caution 24 hours after the last coat is applied.
- Furniture can be placed after 24 hours.
- Allow the moisture to evaporate for minimum three dasys before laying rugs.
- Do not clean floor with water or detergents during the first month.
- Attach felt pads to the legs of chairs and tables in order to avoid scratching the finish.
- The surface must not be covered with non-porous protective materials.

I FINISHING OF UNFINISHED FLOORS OR FLOORS WHERE OLD FINISH MUST BE REMOVED

1. PREPARATION

- Machine sand the surface to remove old treatments and impurities in the wood. The first sanding is made with a coarse sandpaper and high roller pressure.
- Make the floor surface as even as possible. If the floor is uneven in spots, sand locally to even out these areas.
- The final sanding is made with 120-150 grit sandpaper or 100 grit screen, and with the lowest possible roller pressure. If roller pressure is too high, the soft springwood may be compressed. When moisture from the finish affects such softwood, it will raise the grain of the floor by swelling back to its original volume.
- Vacuum and tack the floor before applying the finish. Do not forget to remove dust on skirtings, windowsills, radiators, etc.

2. PRIMING

- Use Synteko SEALMASTER or SEALER for priming (read separate Product Information).
- The first coat is intended to seal the wood. Do not apply too heavy coat on less absorbing kind of wood.
- Do not allow puddles of finish to remain on the floor. If the sealer is poured onto the floor from the container, it must be spread as quickly as possible to prevent the wood from absorbing too much water.
- When sealing, it is practical to have as good ventilation as possible. This will help accelerate the drying time and reduce grain raising. In hot and dry climates, reduce ventilation in order to avoid too quick drying and risk of overlap marks.
- Wait until the wood has an even colour tone before performing intermediate sanding. For intermediate sanding use a screen or paper 150 grit or finer.
- Vacuum and tack the floor before applying Synteko top coats. Do not forget to remove dust on skirtings, windowsills, radiators, etc.

3. MIXING AND POT-LIFE

- Synteko NovaBEST and Synteko Hardener 1648 must be mixed before use (read separate Product information for more detailed information on Synteko Hardener 1648).
- Add 5% or total contents of Hardener 1648 to a full container of Synteko NovaBEST.
- Immediately begin to shake in order to mix in the hardener into the finish. Shake it for at least 30 seconds.
- Let the mixture stand 5 minutes before use in open canister allowing air bubbles to surface.
- Finish mixed with hardener must be used within 4 hours.
- The container must be kept open after addition of hardener.
- Shake well before use!

4. FINISHING

- Work gently with the applicator or roller, thus minimizing the amount of air mixed into the finish. When using an applicator, use the "snow plow" method in continuous, steady movements.
- Be careful in corners and other places where finish may be applied in increased amounts. Use a smaller brush in such areas.
- If the relative humidity of the air is high and/or the temperature is low, reduce the amount of finish used. If the humidity of the air is low and/or the air temperature is high, increase the amount of finish used.
- Always avoid direct sunshine on the floor, which may heat the hardwood resulting in too quick drying.
- When the whole surface has been completed, leave doors ajar. Avoid direct air drafts over the surface of the floor. Normal airflow is sufficient for the drying of the finish.



- If further coats are desired, let the finish dry for 2 to 4 hours and if necessary do the intermediate sanding, use a screen or paper 150 grit, vacuum cleaning and apply the finish as described above.
- However, do not apply more than two coats per day (sealer and/or finish) in order to allow the finish to dry and cure as soon as possible.
- If the floor has been drying more than 24 hours, intermediate sanding is necessary.
- Please note that sanding of earlier layer becomes difficult after 3rd day – it is caused by ceramic particles providing extra scratch resistance

II RE-FINISHING OF PREVIOUSLY FINISHED FLOORS

1. PREPARATION

- An absolute requirement for re-finish or touching up a previously finished surface is that it is free of grease, polish or similar substances.
- If the floor has been waxed, it should be sanded well down to bare wood prior to finishing.
- If the floor has been treated with polish, an adhesion test must be carried out. First, a small area is coated with finish. After it has dried, scraping the area with the edge of a coin tests the adhesion. If the finish layer loosens, it did not adhere correctly, and complete sanding to bare wood is necessary.
- Before re-finishing clean with Synteko REMOVER
- Then clean with 10% vinegar in 90% water to remove all residues of grease, polishes, etc. and finally wipe the floor with pure water.
- Sand or screen with a 150 grit or finer to obtain a matte surface.
- Vacuum clean thoroughly.
- 2. FINISHING
 - Apply one or two coats of Synteko waterbased top finish following instructions described in chapter I.
 - Do not apply more than one coat a day.

III TREATMENT OF UV-CURED FLOOR FINISHES

1. PREPARATION

- Sand or screen the floor using a very fine paper (150-200 grit) or an abrasive pad. Screen the surface until it has turned matte.
- Vacuum thoroughly, and tack the surface with a damp clean cloth to completely remove all the dust.
- An adhesion test must be carried out. First, a small area is coated with finish. After it has dried, scraping the area with the edge of a coin tests the adhesion. If the finish layer loosens, it did not adhere correctly, and complete sanding to bare wood is necessary

2. FINISHING

• Apply one or two coats of Synteko waterbased top finish following instructions described in chapter I.

SYNTEKO WATERBASED FINISHES CARE AND MAINTENANCE



Surfaces treated with Synteko floor finishes are easy to keep clean. Vacuum cleaning and, if necessary, mopping with a **Synteko SUPER CLEAN 1697** solution and a well wrung cloth is normally sufficient. Marks from rubber heels, shoe polish, lipstick, ink, etc. should be removed immediately with **Synteko REMOVER 1692** or with mineral spirits. Avoid scrubbing with coarse brush or strong detergents.

Periodic use of **Synteko NEWSHINE 1696** in high traffic areas will help to protect the floor. Synteko NEWSHINE can also be used to restore light scratch marks.

HOW DO I USE SUPER CLEAN 1697?

- 1. Vacuum or mop the floor to remove any dirt.
- 2. Prepare Synteko SUPER CLEAN as follows:
 - For normal cleaning, 1 part Synteko SUPER CLEAN to 50 parts water
 - For heavy cleaning, 2–3 parts Synteko SUPER CLEAN to 50 parts water
- 3. First, pour the water into a bucket. Never pour water directly onto a wood floor.
- 4. Dip a soft cloth or a sponge mop into the mixture and wring thoroughly before cleaning the floor.
- 5. Superclean is designed for use also with Spray Mop Kit

Synteko SUPER CLEAN is suitable for wet mops and combimachines.

HOW DO I USE NEWSHINE 1696?

- 1. Before applying Synteko NEWSHINE make sure that the floor is clean.
- 2. Sweep, mop or vacuum the floor.
- 3. Old soap, grease, polish etc. should be removed by washing with water and Synteko REMOVER.
- Apply Synteko NEWSHINE in a thin, even layer using a damp mop or a non-flocculent cloth. Usage of Spray Mop Kit is possible.
- 5. Leave the floor to dry for app. 30 minutes before walking on it.

HOW DO I USE REMOVER 1692?

- 1. Vacuum or mop the floor to remove any dirt.
- 2. Prepare Synteko REMOVER as follows:
 - For normal cleaning, ½ 1 part Synteko REMOVER to 100 parts water
 - For heavy cleaning, 2–3 parts Synteko REMOVER to 100 parts water
- 3. Soak a cloth in the mixture; do not pour it directly onto the floor.
- 4. Wet mop, let the mixture act for a few minutes and then dry mop. Usage of Spray Mop Kit is possible.
- 5. Further cleaning with 1 part vinegar to 9 parts water is recommended if sanding and recoating is to be done.
- The floor must be completely dry before screening and recoating.

HEALTH & SAFETY INFORMATION

FOR PROFESSIONAL USE ONLY! Detailed information and guidance is provided in our MSDS (Material Safety Data Sheet) www.synteko.com. The following only represents a selection of important information.

Note: Keep out of reach of children. If medical advice is needed, have product container or label at hand. Do not get in eyes, on skin, or on clothing. Call a POISON CENTER or doctor/physician if you feel unwell. Dispose of contents and container in accordance with all local, regional, national or international regulations. Contains 1,2-benzisothiazol-3(2H)-one and 2,4,7,9-tetramethyl-5-decyne-4,7-diol. May cause an allergic reaction. Safety data sheet available on request.

EU limit value for this product (cat. A/j): 140 g/l (2007) / 140 g/l (2010). This product (A+B mix) contains max 90 g/l VOC.

Our information is based on laboratory tests and is considered a guide in connection with choice of product and working method. As your working conditions are beyond our control, we do not assume any responsibility for the results. Our responsibility covers exclusively personal injury and damage to property, which actually have been proved subsequent to faults and defects inone of the products manufactured by us.

Producer: Synteko AB, Olof Wijksväg 9, Jörlanda, Sweden, Tel. +46 303 563 30 www.synteko.com

SYNTEKO STAR, NOVA BEST & SPORT HARDENER 1648



AREA OF USE:

Synteko Hardener 1648 is a crosslinker inteded for use only in combination with Synteko STAR, Synteko NOVA BEST or SPORT, a two-component, waterborne, low-odour hardwood floor finishes for use in high traffic and commercial areas.

MIXING AND POT-LIFE

Add 5% or total contents of Synteko Hardener 1648 to a full container of Synteko STAR, Synteko NOVA BEST or SPORT. Immediately begin to shake in order to mix in the hardener into the finish and shake it for at least 30 seconds. Let the mixture stand five minutes before use, allowing air bubbles to surface. Finish mixed with hardener must be used within 4 hours. The container must be kept open after addition of hardener.

TECHNICAL DATA:

Base material	Polyisocyanate diluted in dipropyleneglycoldimethylether
Solids content	ca. 70%
Density	ca. 1080 kg/m³ (ISO 2811-1)/ (8,68 lb/gal US) (10,42 lb/gal UK)
Fire hazards	Not flammable
Storage	Store frost-free. Must be stored between +10°C (+50°F) and +30°C (+86°F)
Self life	18 months in unopened container from production date (s. package)
Package size	0,24 L (available only together with finish)

HEALTH & SAFETY INFORMATION

Safety data sheet available for professional user on request. Detailed information and guidance is provided in our MSDS (Material Safety Data Sheet) www.synteko.com. The following only represents a selection of important information.

Warning. Harmful if inhalated. May cause an allergik skin reaction. May cause respiratory irritation. Harmful to aquatic life with long lasting effects. Keep out of reach of children. If medical advice is needed, have product container or label at hand. Use only outdoors or in a well-ventilated area. Do not get in eyes, on skin, or on clothing. Avoid breathing vapour. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER or doctor/physician if you feel unwell. Store locked up. Dispose of contents and container in accordance with all local, regional, national or international regulations. Hazardous ingredients: Hexane, 1,6-diisocyanato-, homopolymer, polyethylene glycol mono-Me ether-blocked hexamethylene-di-isocyanate. Contains isocyanates. May produce an allergic reaction.

Our information is based on laboratory tests and is considered a guide in connection with choice of product and working method. As your working conditions are beyond our control, we do not assume any responsibility for the results. Our responsibility covers exclusively personal injury and damage to property, which actually have been proved subsequent to faults and defects inone of the products manufactured by us.

> Producer: Synteko AB, Olof Wijksväg 9, Jörlanda, Sweden, Tel. +46 303 563 30 www.synteko.com

> > Date: 01.08.2021