



INSTITUT PRO TESTOVÁNÍ A CERTIFIKACI, a. s.

třída Tomáše Bati 299, Louky, 763 02 Zlín

CSI Division – Centre of Civil Engineering

Construction Testing Laboratory Zlín, K Cihelně 304, 764 32 Zlín - Louky



Testing laboratory No. 1007.1 accredited by ČIA according to ČSN EN ISO/IEC 17025:2018

Page: 1/3

No. 415602299-01

ACCREDITED LABORATORY TEST REPORT No. 415602299-01

Client: SYNTEKO AB
VAT: SE556571368101

Address: Olof Wiks väg 9, 444 65 Jörlanda, Sweden

Subject of the test: Nordic Elastic

Sample received on: September 21, 2026


Tested: October 5, 2026

Report elaborated by: Ing. Radim Mikač

Place and date of issue: Zlín, October 9, 2026

Annex: -




Ing. Jiří Růžička
Head of Construction Testing Laboratory Zlín


Ing. Petra Hrdinová
Head of Accredited Testing Laboratory

Note: The results given in this Test Report apply only to the sample tested by our laboratory!
Without a written consent by Institut pro testování a certifikaci, a.s. Zlín, the Test Report may not be reproduced unless as a whole!

Subject of the test:
Table No. I – Description and identification of the test Subject

ITC's identification number	Identification of the test Subject/sample by client	Description
415602299/1	Nordic Elastic	Approximately 3 litres of colourless liquid in a plastic container
415602299/2	Hardener	Approximately 0.3 litres of colourless liquid in a plastic container


Fig. No. 1: Nordic Elastic + Hardener
Sampling method used:

The test sample was collected and supplied to the laboratory by the client. The laboratory is not responsible for this way of sampling. The results apply to the sample received.

Work requested:

Determination of the product's anti-slip properties

Testing method used:

Determination of anti-slip surface properties – test by pendulum according to ČSN EN 13036-4

Test conditions:

Tested on October 5, 2026, flat surface without curvature, wide friction foot with rubber No 57 used, friction foot number 1158, test carried out under dry conditions, Nordic Elastic compound mixed with 10 per cent hardener, system applied in two coats

The laboratory is not responsible for information received from customer, which could have influence on the validity of the results. Further information required by the standard/standards and not given in this Test Report are available at a request at the Laboratory.

Testing laboratory:

The test was performed in the workplace no.2: Třída Tomáše Bati 5264, areal Svit, Building No. 113, 760 01 Zlín

Note: The results given in this Test Report apply only to the sample tested by our laboratory!

Without a written consent by Institut pro testování a certifikaci, a.s. Zlín, the Test Report may not be reproduced unless as a whole!



Test results:

The test results is given in the following table:

Table No. II – Nordic Elastic + Hardener

Characteristics measured	Unit	Separate values	Test results	Uncertainty ¹⁾	Required value ²⁾	Evaluation ³⁾
Slip resistance	-	105; 105; 105; 104; 104	105	3	80 to 110 Individual results must not deviate from the overall average by more than 4 units	Compliant

¹⁾ expanded uncertainty for coverage factor $k = 2$, which for a normal distribution corresponds to a coverage probability of approximately 95%

²⁾ Requirement of standard ČSN EN 14904 – Surfaces for sports facilities – Indoor surfaces for multi-purpose use – Specifications, clause 4.2

..... End of the test report.....

Note: The results given in this Test Report apply only to the sample tested by our laboratory!

Without a written consent by Institut pro testování a certifikaci, a.s. Zlín, the Test Report may not be reproduced unless as a whole!